

FULL BODY PORCELAIN STONEWARE - UGL
Gres porcellanato a tutta massa . Grès cérame plaine masse . Vollmassefeinsteinzeug

	NORME TEST N°	DESCRIZIONE DESCRIPTION	VALORE A NORMA REQUIRED STANDARD	VALORE RESULTS
	ISO 10545/2	Lunghezza e larghezza Length and width Longueur et largeur Länge und breite	± 0,5%	Conforme Conforms
	ISO 10545/2	SPESSORE THICKNESS ÉPAISSEUR STÄRKE	± 5%	Conforme Conforms
	ISO 10545/2	Ortogonalità Wedging Orthogonalité Rechtwinklichkeit	± 0,5%	Conforme Conforms
	ISO 10545/2	Planarità Warpage Planèité Ebenflächigkeit	± 0,5%	Conforme Conforms
		Variazioni di tono Shade variations Variations de nuance Tonvariationen		 V2 LIEVE VARIAZIONE SLIGHT VARIATION LEGERE VARIATION GERINGE ABWEICHUNG
	ISO 10545/3	Assorbimento d'acqua Water absorption Absorption d'eau Wasseraufnahme	≤ 0,5%	Conforme Conforms
	ISO 10545/4	Resistenza alla flessione Bending strength Resistance a la flexion Biegefestigkeit	R > 35 N/mm²	Conforme Conforms
	ISO 10545/11	Resistenza al cavillo Crazing resistance Resistance au trassailage Haarrissfestigkeit		Resiste Resistant Résiste Beständig
	ISO 10545/13	Resistenza all'attacco chimico Chemical resistance Resistance à l'attaque chimique Fähig gegen säuren und laugen	min. gb	SOFT Classe A-LA Class A-LA Classe A-LA Gruppe A-LA TECH / R11 Classe A-LA-HA Class A-LA-HA Classe A-LA-HA Gruppe A-LA-HA
	ISO 10545/14	Resistenza alle macchie Stain resistance Resistance aux taches Fleckenfestigkeit	min 3	Classe 5 Class 5 Classe 5 Gruppe 5
	ISO 10545/12	Resistenza al gelo Frost resistance Resistance au gel Frostbeständigkeit		Resiste Resistant Résiste Beständig
	ISO 10545/6	Resistenza all'abrasione profonda Deep abrasion resistance Résistance à l'abrasion profonde Tiefenverschleissbestaendigkeit	< 175 mm³	< 175 mm³
	DIN EN 16165 ANNEX B DIN EN 16165 ANNEX A B.C.R.A. REP. CEC. 6/81 ANSI A 326.3 Acu Test	Resistenza alla scivolosità. Coefficiente di attrito medio Skid resistance. Average coefficient of friction Résistance au glissement. Coëfficient de frottement moyen Rutschfestigkeit. Mittlerer Reibungswert	DIN EN 16165 ANNEX B DIN EN 16165 ANNEX A B.C.R.A. REP. CEC. 6/81 ANSI A 326.3 Acu Test	SOFT R9 TECH R10 R11
		Resistenza della superficie (scala MOHS) Scratch hardness (MOHS scale) Dureté de la surface (échelle MOHS) Oberflächenhärte (MOHS skala)	EN 101	≥ 5 ≥ 6 ≥ 6

* THESE VALUES MAY VARY FROM LOT TO LOT.