

| | STANDARD | RESULT |
|---|------------------------------------|--|
| Dimensions and basic data | | |
|  SIZE | EN ISO 24342 | STANDARD PANELS: 900 x 450 mm |
|  THICKNESS | EN ISO 24346 | 4,5 mm |
|  WEAR LAYER | EN ISO 24340 | 0.12 mm |
| LOCKING METHOD | | T&G |
| SURFACE TREATMENT | | PU coating + protected with aluminium oxide (anti-scratch) and stain resistant technology. |
| CORE | | Water resistant rigid core, SPC |
| Technical data – CE EN 15102 | | |
|  BEVELLED EDGE | MICRO | 4 Sides |
|  MASS | ISO 23977 | 9.00 kg/m ² |
|  REACTION TO FIRE | EN 13501-1 | B-s3,d0 |
|  LIGHT FASTNESS | EN ISO 105-B02 | ≥ 6 |
|  DIMENSIONAL STABILITY | EN ISO 23999 | ≤ 0.12 % |
|  STAINING RESISTANCE | ISO 26987 | PASS |
| CURLING RESULTANT TO HEAT | ISO 23999 | ≤ 1.2 mm |
| Dangerous substances | | |
|  VOC EMISSION | French/belgian/ german Regulations | PASS |
|  FORMALDEHYDE EMISSION | EN 717-1 | E1 |
| REACH | | Friendly reach compliant |
| HEAVY METALS | EN 71-3 | PASS |
|  PCP | EN 12673 | PASS |